

# HydroBlock® 22a 2000 I

HydroBlock® 22a 2000 I is a poly-chloro-trifluoroethylene copolymer, high performance barrier film for industrial and electronics applications. It provides outstanding water vapor barrier and excellent chemical resistance with high clarity.

Properties at 73°F(23°C) - 50%RH	Typical Value		Test Method
	English	Metric	
Specific Gravity	2.08	2.08	ASTM D1505
Yield	6,667 in <sup>2</sup> /lb	9.48 m <sup>2</sup> /kg	-----
Haze	<1%	<1%	ASTM D1003
Crystalline Melting Point	373°F	190°C	ASTM D4591
Dimensional Stability MD 300°F/149°C/10 min TD	≤ +15% ≤ -15%		ASTM D1204
Tensile Strength MD TD	8,000 - 12,000 psi 6,000 - 8,000 psi	55 - 83 MPa 41 - 55 MPa	ASTM D882
Elongation MD TD	125 - 200% 225 - 300%		ASTM D882
Modulus MD TD	150,000 - 180,000 psi 150,000 - 180,000 psi	1034 - 1241 MPa 1034 - 1241 MPa	ASTM D882
Water Vapor Transmission Rate @ 100°F(37.8°C)/100%RH	0.016 gms/100in <sup>2</sup> /day	0.25 gms/m <sup>2</sup> /day	ASTM F1249

**Manufactured by Honeywell International**

**Distributed by: TEXAS TECHNOLOGIES, INC.**

3600 W. Whitestone Blvd. Cedar Park, Texas 78613

800.858.1379 or 512.267.0100

E-Mail: [info@texastechnologies.com](mailto:info@texastechnologies.com)

Website: [www.texastechnologie.com](http://www.texastechnologie.com)

**DISCLAIMER:** Although Honeywell International Inc. believes that the values and information contained herein is accurate and reliable, it is not intended to be product specifications, and are presented without guarantee or responsibility of any kind and does not constitute any representation or warranty from Honeywell, whether express or implied. A number of factors can affect the selection and use of films. Nothing presented herein shall relieve the user from the responsibility of carrying out its own assessment, verification, and safety protocols. Any information and technical support provided by Honeywell is gratuitous in nature and offered without any warranties or representation. The user assumes all risks and liability for the use of the information contained herein, including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment.

HydroBlock® is a registered trademark of Honeywell International Inc.

March 2014

