



— D —

D

L

L

Meets the required limits of ANSI/ESD S20.20, Packaging standard ANSI/ESD S541 tested per ANSI/ESD STM11.11, ESD TR53 and ANSI/ESD STM11.31

SPECIFICATIONS

Properties

Surface Resistance

Discharge Shielding

Sloughing Test

Recyclability

Typical Values

1×10^6 to $< 1 \times 10^9$ ohms

< 50 nJ

Negligible surface damage at 10 cycles and <5% of surface damage at 200 cycles in Taber Abrasion Test.

No conductive particles abraded from surface

Complete recyclability of package

Test Procedures/Method

ANSI/ESD STM11.11 and ESD TR53

ANSI/ESD STM11.31

ASTM D4060 at 70 rpm with CS-17 abrasive-coated wheels and 1000 grams load

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992



Made in the
United States of America

RoHS 2, REACH, and Conflict Minerals Statement

None of the RoHS 2 restricted materials, or REACH substances of very high concern as of 2015/06/15, or Conflict Minerals are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See Protective Pak [terms and conditions](#).

REEL STORAGE CONTAINERS

TEXAS TECHNOLOGIES

DRAWING NUMBER
37561

DATE:
September 2015