

CFB 9604 LDPE PINK AS

Specification Sheet

This anti-static product is specially designed for packaging applications that require exceptional cleanliness and meet the anti-static film's requirements. Our anti-static poly film is AMINE-FREE and is available in colors.

Material	Virgin Barefoot Custom Polyethylene
Available As:	Lay-flat tubing, Sheeting & Bags
Clarity:	Transparent
Thickness:	.002", .004", & .006" Custom gauges are available upon request.

Properties	Value	Specification
Density (Specific Gravity)	.924	ASTM D 1505
Tensile Strength @ Break		ASTM D 882
MD	2900 PSI	
TD	2300 PSI	
Elongation Strength		ASTM D 882
MD	325%	
TD	425%	
Dart Impact	80 Grams	ASTM D 1709
Cleanliness	LVL 50 & LVL 100	IEST-CC-1246 NASA JPR5322.1G
Surface Resistivity	<10 ¹¹ OHMS/SQ.	ASTM D 257

Note: All values, unless otherwise noted, are based on a 2.0 mil thick film

TEXAS TECHNOLOGIES, INC.
3600 W. Whitestone Blvd. Cedar Park, TX 78613
800.858.1379 or 512.267.0100
E-Mail: info@texastechnologies.com
www.texastechnologies.com

Specification Sheet (cont.)

Leachable Anions by IC

Analyte	Reporting Limit (ng/cm ²)	Sample Results (ng/cm ²)
Bromide	0.2	*
Chloride	0.1	0.2
Fluoride	0.03	*
Nitrate	0.2	*
Nitrite	0.1	*
Phosphate	0.2	*
Sulfate	0.2	*

* - Reported results are less than the reporting limit

Leachable Monovalent & Divalent Cations by IC

Analyte	Reporting Limit (ng/cm ²)	Sample Results (ng/cm ²)
Lithium	0.2	*
Sodium	0.1	*
Ammonium	0.2	*
Potassium	0.2	*
Magnesium	0.2	*
Calcium	0.2	*

* - Reported results are less than the reporting limit

NVR

“LDPE PAS” Sample	10.3 ug/cm ²
-------------------	-------------------------

Leachable Laser Particle Count

Leaching Volume=300 ml / Surface Area=948 cm² / Leaching Time = 1 HR.

	Measured (counts/cm ²)
Particles >= 0.3 um	470
Particles >= 0.5 um	75
Particles >= 0.75 um	25
Particles >= 1.0 um	7.4
Particles >= 2.0 um	1.5
Particles >= 5.0 um	0.2