



SURFACE PREPARATION PRODUCTS

VpCI® Super Penetrant



PRODUCT DESCRIPTION

Cortec® VpCI® Super Penetrant offers a deep penetrating formulation that loosens frozen parts locked in rust. Its deep penetrating capabilities allow the user to go through as much as 1/2 inch (13 mm) of rust in 30 minutes. VpCI® Super Penetrant can be applied by a variety of convenient methods to meet any application needs including brush, hand pump spray, aerosol, spray application, or dipping.

As VpCI® Super Penetrant breaks through deep rust, it displaces moisture and water. Its superior surface wetting and moisture displacing properties allow it to spread rapidly and get underneath the moisture layer normally present on metal under atmospheric conditions. While loosening the rust, it lubricates metal so frozen parts can move freely. Utilizing patented Cortec® VpCI® technology, the VpCI® Super Penetrant forms an ultra thin film on metal that offers 6 months of protection from corrosion in extreme conditions.

Cortec® VpCI® Super Penetrant can be used for indoor and outdoor applications. Its superior water displacing characteristics make it an ideal choice for applications of equipment and components that are exposed to outside weather. It also conforms to Federal Specifications for VV-P-216 Penetrating Oil for Loosening Frozen Metallic Parts and ASTM D-971 Test for Interfacial Tension of Oil against water.

FEATURES

- Provides universal corrosion protection for ferrous metals, galvanized steel, aluminum, brass, copper, babbitt, zinc, cadmium, and silver
- Loosens frozen and rusted metal parts making them easy to remove

TYPICAL APPLICATIONS

- Maintenance
- Lubrication
- Temporary storage - spray a light coating on flat metal before or after metalworking
- Small or complex metal parts - spray on or dip in
- General surface treatment - spray, dip, or brush surfaces to be protected for up to 24 months
- Home repairs of squeaky items

TYPICAL PROPERTIES

Appearance	Clear amber liquid
Film Type	Oily
Flash Point	170°F (77°C)
Removal Methods	Alkaline cleaners and solvents (VpCI-416/VpCI-419)
Density	6.8-7.0 lb/gal (0.82-0.84 kg/l)
Non-volatile Content	30-40%

PROTECTION PROPERTIES

VpCI® Super Penetrant displaces water as effectively as a leading lubricating rust preventive (R.P.) oil while providing much better protection against corrosion.

	Time Before Corrosion								Water Displacing per MIL-C-83933	
	Salt Spray (Days) ASTM B-117			Humidity Test (Days) ASTM D-1748						
	Carbon Steel	Aluminum	Copper	Carbon Steel	Cast Iron	Aluminum	Copper			
VpCI® Super Penetrant	5	15+	5	30+	10+	50+	50+		Pass	
Leading Lubricating/R.P. Oil	5	15+	3	30+	1	50+	50+		Pass	

STANDARD TEST METHODS

ASTM D-971	Test for Interfacial Tension of Oil against Water
ASTM B-117	Salt Spray
ASTM D-1748	Humidity Test
NACE RP0487-2000	Selection of Rust Preventives

PACKAGING AND STORAGE

VpCI® Super Penetrant is packaged in 5 gallon (19 liter) pails, 55 gallon (208 liter) metal drums, liquid totes, and bulk. It is also available in aerosol form net weight 5.25oz (148.84g). The product should be stored sealed. Agitate before each use. Shelf life is up to 24 months.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT SAFETY DATA SHEET FOR MORE

INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE,

AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Distributed by:

TEXAS TECHNOLOGIES, INC.

3600 W. Whitestone Blvd. Cedar Park, TX 78613

800.858.1379 or 512.267.0100

E-Mail: info@texastechnologies.com

www.texastechnologies.com

Printed on recycled paper  100% post consumer

Revised: 11/14/16. Supersedes: 05/02/06. ©Cortec Corporation 2002-2016 of Cortec Corporation.
All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. 2016, ©Cortec Corp. ISO accreditation applies to Cortec's processes only.